Chemical	Rating	Chemical	Rating
1,4-Dioxane, pure	X	Aluminum sulfate, 10%	А
2,2,4-Trimethylpentane, pure ⁴	Α	Aluminum chloride, pure	А
2,4,6-Trinitrophenol	X	Aluminum hydroxide	В
2-Methoxyethanol	X	Aluminum salts, pure	Α
2-Propanol, pure ⁴	Α	Aluminum trichloride, 10%	А
Acetaldehyde	X	Amino acid, pure	Α
Acetamide	X	Aminoethanol (2-)	А
Acetic acid, 5%	Α	Ammonia, 25% ²	А
Acetic acid, 10%	Α	Ammonia, 29% ²	А
Acetic acid, 20%	Α	Ammonia ⁴	В
Acetic acid, 50% ¹	Α	Ammonium acetate, saturated	А
Acetic acid, glacial ¹	Α	Ammonium chloride, 10%	А
Acetic anhydride	Х	Ammonium chloride, pure	Α
Acetone, 5%	Α	Ammonium glycolate, pure	Α
Acetone, 50%	Α	Ammonium hydroxide, 5% ¹	Α
Acetone, 60% ²	Α	Ammonium hydroxide, 15% ¹	Α
Acetone, pure	Х	Ammonium hydroxide, 29% ¹	Α
Acetonitrile	X	Ammonium hydroxide, 30% ¹	Α
Acetophenone	Х	Ammonium nitrate, 10%	Α
Acetyl chloride	X	Ammonium oxalate, pure	Α
Acrylonitrile	Х	Ammonium persulfate, 24%	Α
Adhesive (Eastman 910)	Α	Ammonium salts, pure	А
Adipic acid, pure	А	Ammonium sulfate, 10%	А
Alanine, pure	A	Amyl acetate	Х
Alconox, 1%	А	Amyl alcohol	А
Allyl alcohol ⁴	В	Amyl alcohol, pure	Α

A = Little or no interaction B = Slight interaction X = Not recommended Room temperature = 20°C or 68°F (1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer



⁽³⁾ Prolonged exposure may reduce resistance --- (4) Room Temperature only

ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
Amyl chloride	X	Butadiene	Х
Aniline	X	Butanol ²	А
Anti-Freeze ²	Α	Butter, salted²	А
Antimony trichloride	X	Butyl acetate	Х
Aqua regia, pure	X	Butyl alcohol	А
Automotive grease ²	Α	Butyl cellosolve	А
Aviation gasoline (100 octane) ³	В	Butyl chloride	Х
Barbitol solvent	Α	Butyl ether	А
Barium chloride, 10%	Α	Butyl phthalate	Х
Benzaldehyde	X	Butylamine (n-)	Х
Benzenamine	X	Butylated hydroxy anisole	Х
Benzene	X	Butylated hydroxy toluene	А
Benzene sulfonic acid	X	Butyraldehyde	Х
Benzoic acid ³	В	Butyric acid	Х
Benzol, pure	X	Calcium chloride, saturated	А
Benzonitrile	X	Calcium dinitrate, 10%	А
Benzyl acetate	X	Calcium hydroxide	В
Benzyl alcohol	X	Calcium hypochlorite, 3.5% ³	А
Benzyl chloride	X	Calcium hypochlorite, saturated ³	А
Black liquor ¹	Α	Calcium propionate ²	А
Boric acid	Α	Calgon liquid	А
Brake fluid	X	Carbitol	А
Brine	Α	Carbazole	Х
Bromine, 10% ^{1,3}	В	Carbon disulfide	Х
Bromine, pure	X	Carbon tetrachloride ³	А
Bromobenzene	X	Carbon Tetrachloride	Х
Bromoform	X	Caustic potash, 30% ⁴	А
A = Little or no interaction B = Slight interaction	X = Not recommende	d Room temperature = 20°C or 68°F	

(1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only



ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
Caustic potash, 50%4	Α	Citric acid, 1M	Α
Caustic potash, concentrated ⁴	Α	Copper sulphate, pure	А
Caustic soda, 1%	Α	Corn oil ²	А
Caustic soda, 50% ¹	Α	Cotton Seed oil ²	А
Cedarwood oil ³	В	Cresol (m-)	Х
Cellosolve (2-ethoxyethanol)	Α	Cresol	Х
Cellosolve acetate	X	Cresyl Diphenyl phosphate	Х
Cellosolve solvent ⁴	A	Cupric chloride, saturated	А
Chlorine, water solution	X	Cyclohexane ²	А
Chlorine, dry gas, 10%	X	Cyclohexane	Х
Chlorine, wet gas	X	Cyclohexanol	А
Chlorine, wet gas, 10%	X	Cyclohexanone	Х
Chloroacetic acid	X	Cyclopentane	Х
Chlorobenzene	X	Decahydronaphthalene	Х
Chloroethanol (2-)	X	Decalin, pure	Х
Chloroform	X	Diacetone, pure	Х
Chlorophenol, 5%	X	Diacetone alcohol	Х
Chromic acid, 10% ²	Α	Dibutyl phthalate, pure	Х
Chromic acid, 12% ²	Α	Dichlorobenzene (p-), vapor	Х
Chromic acid, 20%	X	Dichlorodifluoromethane (Freon 12)	А
Chromic acid, 50%	X	Dichloromethane	Х
Chromic acid, 60%	X	Diesel fuel	А
Chromic acid, sulfuric acid mixture, 96%	X	Diesel fuel (fuel oil #2)	А
Cinnamon oil ³	В	Diethyl benzene	Х
Citric acid, 2%	Α	Diethyl ether	Х
Citric acid, 10%	Α	Diethyl ketone	Х
Citric acid, 40%	Α	Diethyl malonate ³	В
A = Little or no interaction B = Slight interaction	X = Not recommende	Room temperature = 20°C or 68°F	

(1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only



ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
Diethylamine ^{1,3}	В	Ethyl benzoate	Х
Diethylene dioxide	X	Ethyl butyrate	Х
Dimethyl formamide	X	Ethyl chloride	Х
Diethylene glycol	X	Ethyl cyanoacetate	Х
Diethylene glycol monoethyl ether	X	Ethyl lactate	Х
Dimethyl acetamide, pure	X	Ethylbutyric acid (2-)	А
Dimethyl formamide, pure	X	Ethylene chloride	Х
Dimethyl sulfoxide	X	Ethylene dichloride	Х
Dimethylaniline	X	Ethylene glycol	А
Dimethylformamide (N,N-)	X	Ethylene glycol, pure	А
Dimethylsulfoxide, 50% (DMSO)	В	Ethylene glycol monomethyl ether	Х
Dimethylsulfoxide, pure (DMSO)	X	Ethylene oxide	А
Dioctylphthalate ² (dioctyl phthalate)	А	Ethylene oxide, gas	А
Dioxane (p-)	X	Ethylene oxide, pure	А
Dipropylene glycol ³	В	Ethylenediamine, 92% ⁴	А
DMSO	X	EtO, gas (ethylene oxide)	А
Dowtherm	X	EtO, pure (ethylene oxide)	А
Epichlorohydrin	X	Fatty acids - saturated	В
Ethanol ^{1,2}	Α	Fatty acids - unsaturated	В
Ethanol, 40% ^{1,2}	В	Ferric chloride, 10%	А
Ether	X	Ferrous sulfate, saturated	А
Ethyl acetate	X	Fluorides	А
Ethyl alcohol, 15%	Α	Fluorine, gas	Х
Ethyl alcohol, 40% ^{1,2}	В	Formaldehyde, 2%	А
Ethyl alcohol, 95% ^{1,2}	В	Formaldehyde, 30%	А
Ethyl alcohol, pure ^{1,2}	В	Formaldehyde, 10%	Α
Ethyl benzene	Х	Formaldehyde, 37% ¹	А
A = Little or no interaction B = Slight interaction	X = Not recommended	Room temperature = 20°C or 68°F	

A = Little or no interaction B = Slight interaction X = Not recommended Room temperature = $20^{\circ}C$ or $68^{\circ}F$ (1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer



⁽³⁾ Prolonged exposure may reduce resistance --- (4) Room Temperature only

ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
Formaldehyde, 40% ¹	Α	Hexane ¹	В
Formalin, 10%	Α	Hexanol	А
Formalin, 40% ^{1,3}	В	Hydraulic oil	А
Formic acid, 3% ¹	A	Hydrazine	Х
Formic acid, 10% ¹	В	Hydrobromic acid, 20%	А
Formic acid, 25% ¹	В	Hydrobromic acid, 69% ¹	А
Formic acid, 50% ¹	В	Hydrochloric acid, 5%²	А
Formic acid, 88% ¹	X	Hydrochloric acid, 20% ²	А
Formic acid, 100% ¹	X	Hydrochloric acid, 37% ¹	А
Formic acid, pure ¹	X	Hydrofluoric acid, 4% ^{1,3}	В
Freon 11 ¹	А	Hydrofluoric acid, 25% ^{1,3}	А
Freon TF, pure ¹	В	Hydrofluoric acid, 50% ^{1,3}	А
Freon TMC	X	Hydrogen peroxide	А
Freon TMS ²	A	Hydrogen peroxide, 3%	А
Fuel oil ¹	Α	Hydrogen peroxide, 30%	А
Furfural	X	Hydrogen peroxide, 90%	А
Gasoline ²	Α	lodine solutions	Х
Glutaraldehyde	В	Isobutanol, pure ¹	А
Glutaraldehyde disinfectant	В	Isobutyl alcohol	А
Glycerin, pure	Α	Isobutyl alcohol, pure ¹	А
Glycerol, pure	Α	Isooctane	А
Grape juice	Α	Isopropanol ^{1,3}	В
Grease ²	Α	Isopropanol, 100% ^{1,3}	В
Green liquor	Α	Isopropanol, pure ^{1,3}	В
Heptane (n-) ²	Α	iso-Propanol, 100% ^{1,3}	В
Heptane, 0.05%	Α	Isopropyl acetate	Х
Hexane (n-) ²	В	Isopropyl alcohol	А
A = Little or no interaction B = Slight interaction	X = Not recommended	Room temperature = 20°C or 68°F	

A = Little or no interaction B = Slight interaction X = Not recommended Room temperature = 20°C or 68°F

(1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only



ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
Isopropyl alcohol, 100% ^{1,3}	В	MEK, pure	Х
Isopropyl alcohol, pure ^{1,3}	В	Methanol ²	А
Isopropyl benzene	Х	Methanol, 100% ²	Α
Isopropyl ether ³	В	Methoxyethyl oleate	Х
Isopropyl ether, pure	Х	Methyl acetate	Х
Jet fuel (640A)	A	Methyl alcohol ²	Α
Jet fuel (JP-4)	А	Methyl alcohol, 98% ¹	В
Jubilee wax ⁴	A	Methyl alcohol, pure ¹	В
Kerosene ²	А	Methyl cellosolve	Α
Ketchup	A	Methyl chloride	Х
Lacquer thinner	Х	Methyl ethyl ketone	Х
Lactic acid, 3%	A	Methyl formate	Х
Lactic acid, 60% ³	А	Methyl isobutyl ketone	Х
Lactic acid, 85% ³	A	Methyl propyl ketone	Х
Lard	А	Methylene chloride	Х
Lauric acid ³	A	Methylpyrrolidone	Х
Lead acetate, pure	А	Methyl-t-butyl ether	Х
Lemon oil	С	MIBK	Х
Lestoil	С	Milk ²	Α
Linseed oil	A	Mineral oil	Α
Lubricating oil	А	Mineral spirits ^{3,4}	В
Magnesium chloride, 10%	A	Monochlorobenzene	Х
Magnesium chloride, pure	А	Monochlorodifluoromethane (Freon 22) ³	В
Malonic acid	A	Monoethanolamine	Α
Margarine ²	А	Morpholine, 0.2%	Х
Mayonnaise	А	Motor oil	Α
MEK, 40% ²	А	Mustard	Α
A = Little or no interaction B = Slight interaction	X = Not recommended	Room temperature = 20°C or 68°F	

A = Little or no interaction B = Slight interaction X = Not recommended Room temperature = $20^{\circ}C$ or $68^{\circ}F$ (1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only



ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
N-amyl acetate	X	Oil (ASTM #1)	А
N-butanol ^{3,4}	В	Oil (ASTM #2)	А
N-butyl acetate	X	Oil (ASTM #3) ²	А
N-butyl alcohol ^{3,4}	В	Oil, cedarwood ^{2,3}	В
N-decane ^{3,4}	В	Oil, cinnamon ^{2,3}	В
N-Heptane ¹	Α	Oil, corn ²	А
N-methyl-2-pyrrolidone	X	Oil, mineral ¹	А
NALCON 7330 (<1%)	Α	Oil, olive ³	А
NALCON 7647 (<1%)	Α	Oil, orange ^{2,3}	В
NALCON 7678 (<1%)	Α	Oil, pine ^{2,3}	В
Naphtha VMOP	X	Oil, vegetable²	Α
Naphthalene, vapor	Х	Oleic acid ²	А
Nitric acid, 5% ^{3,4}	В	Olive oil ³	Α
Nitric acid, 10% ^{3,4}	В	Orange oil ^{2,3}	В
Nitric acid, 20% ^{3,4}	В	Oxalic acid, 10%	Α
Nitric acid, 25% ^{3,4}	В	Oxalic acid, 20%	А
Nitric acid, 40% ^{3,4}	В	Oxygen	Α
Nitric acid, 50% ^{3,4}	В	Ozone	А
Nitric acid, 71%	X	Ozone, pure	Α
Nitric acid, 6N	Х	P-chloroacetophenone	X
Nitro Methane	X	P-dichlorobenzene	X
Nitrobenzene	Х	Peanut oil ²	А
Nitrobenzene	X	Pentane	А
Nitromethane	X	Peracetic acid, 0.1N	А
Nitropropane	Х	Perchloric acid	Х
N-octane ^{3,4}	В	Perchloroethylene	Х
O-dichlorobenzene	Х	Permatex ²	Α
A = Little or no interaction B = Slight interaction	X = Not recommend	led Room temperature = 20°C or 68°F	

(1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only



ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
Petroleum ^{2,3}	X	Propane, gas ^{2,3}	В
Petroleum based oils	A	Propanol	А
Petroleum ether	А	Propionic acid ³	В
Phenol	X	Propylene glycol, pure ³	В
Phosphoric acid, 5%	А	Propylene oxide, pure ³	В
Phosphoric acid, 20%	A	Pyridine	Х
Phosphoric acid, 85%	Α	Resorcinol	Х
Photographic film developer	A	Resorcinol, 5%	Х
Photographic film fixer	А	Resorcinol, saturated	Х
Picric acid	X	Salicylaldehyde, pure ^{2,3}	В
Pine oil ^{2,3}	В	Salicylic acid, powder	А
Polyalkylene glycol oil (PAG)	X	Salicylic acid, saturated	А
Polyalphaolefin oil (PAO)	А	sec-Butanol, pure¹	А
Polyolester oil (POE)	X	sec-Butyl alcohol, pure ¹	А
Potassium chloride	А	Silastic 140	А
Potassium chloride, pure	А	Silicone compounds ²	А
Potassium Hydroxide, 1%	А	Silicone oil ²	А
Potassium hydroxide, 20%	А	Silver acetate, pure	А
Potassium hydroxide, 25% ¹	Α	Silver nitrate, pure	А
Potassium hydroxide, 30% ^{1,3}	А	Skydrol LD4 aviation hydraulic fluid	Х
Potassium hydroxide, 35%1,3	А	Sodium acetate, pure	А
Potassium hydroxide, 50%1,3	A	Sodium bicarbonate, 10%	А
Potassium hydroxide, 1N ^{1,3}	А	Sodium carbonate, 10%	А
Potassium hydroxide, concentrated ^{1,3}	А	Sodium carbonate, pure ¹	А
Potassium nitrate, saturated	А	Sodium chloride, 10%	А
Potassium permanganate, 10%	А	Sodium chromate, 10%	А
Potassium permanganate, pure	Α	Sodium dichromate, pure	А
A = Little or no interaction B = Slight interaction	X = Not recommended	Room temperature = 20°C or 68°F	

A = Little or no interaction B = Slight interaction X = Not recommended Room temperature = $20^{\circ}C$ or $68^{\circ}F$ (1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only



ver 17-Jan-2023

Chemical	Rating	Chemical	Rating
Sodium hydroxide, 0.1N	Α	Sulfuric acid, 25% ³	А
Sodium hydroxide, 1%	A	Sulfuric acid, 30% ³	А
Sodium hydroxide, 5%	Α	Sulfuric acid, 60% ³	Α
Sodium hydroxide, 10% ¹	Α	Sulfuric acid, 65% ³	А
Sodium hydroxide, 15% ¹	А	Sulfuric acid, 85% ³	Α
Sodium hydroxide, 25% ¹	A	Sulfuric acid, 95%	Х
Sodium hydroxide, 30% ¹	А	Sulfuric acid, 96%	Х
Sodium hydroxide, 50% ¹	A	Sulfuric acid, 98%	Х
Sodium hydroxide, concentrated	А	Sulfuric acid, 6N	Х
Sodium hypochlorite, 0.17%	Α	Sulfuric acid, concentrated	Х
Sodium hypochloride, 10%	А	Surfactant (Jet-Dry)	А
Sodium hypochlorite, 15%	A	Tartaric acid, pure	А
Sodium silicate, 1.7% ²	А	TCA, pure ²	В
Sodium sulfate, 10%	A	tert-Butanol, pure ^{1,2}	В
Sodium sulfide, 10%	А	tert-Butyl alcohol, pure ^{1,2}	В
Sodium thiosulfite, 10%	A	Tetrachlorodifluoroethane (Freon BF) ²	Α
Sorbic acid	А	Tetrahydrofuran (THF)	Х
Stearic acid ^{2,3}	В	THF	Х
Stoddard Solvent ²	А	Thionyl chloride	Х
Sulfolane	X	Toluene	Х
Sulfur dioxide, liquid (46 psig) ^{2,3}	В	Toluene, 0.05% ³	В
Sulfur dioxide, wet gas ^{2,3}	В	Tomato juice	А
Sulfur dioxide, pure ^{2,3}	В	Transmission oil	А
Sulfur salts ^{2,3}	В	Tributyl citrate ^{1,2}	В
Sulfuric acid, 5% ³	А	Trichloroacetic acid, 25%	А
Sulfuric acid, 6% ³	Α	Trichloroacetic acid ^{1,2}	В
Sulfuric acid, 20% ³	Α	Trichlorobenzene	Х
A = Little or no interaction B = Slight interaction	X = Not recommende	Room temperature = 20°C or 68°F	

(1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only



ver 17-Jan-2023

Chemical	Rating
Trichloroethane (1,1,1-) ²	В
Trichloroethane, pure	Х
Trichloroethylene	Х
Trichlorofluoroethane (Freon TF)	Α
Triethylamine	Х
Triethylene glycol, pure	А
Triphenylphosphite	Х
Tripropylene glycol, pure	А
Tris Buffer Solution, pH 11 ^{1,2}	В
Tris Buffer Solution, pH 7.0 ^{1,2}	В
Trisodium phosphate	В
Turpentine	Х

Chemical	Rating
Undecyl alcohol ^{2,3}	В
Urea	Α
Urea, 6N	X
Urea, pure	X
Varsol ²	А
Vegetable oil ²	Α
Vinylidene chloride	X
Water	Α
Xylene ^{2,3}	X
Xylene, pure	X
Zinc chloride, saturated	Α

A = Little or no interaction B = Slight interaction X = Not recommended Room temperature = 20°C or 68°F

(1) Elevated temperatures may reduce resistance --- (2) Exposure to elevated stress may damage polymer

(3) Prolonged exposure may reduce resistance --- (4) Room Temperature only

