

PVDF (Kynar®) Chemical Compatibility Chart

Chemical	Rating
Acetaldehyde	D
Acetamide	C
Acetate Solvents	A
Acetic Acid	C
Acetic Acid, 10% aqueous	A
Acetic Acid, 20% aqueous	A
Acetic Acid, 50% aqueous	A
Acetic Acid, 80% aqueous	C
Acetic Acid, glacial, anhydrous	A
Acetic Anhydride, dilute	B
Acetic Anhydride	D
Acetoacetic Ester	D
Acetone, dilute	D
Acetone	D
Acetonitrile, dilute	A
Acetophenone, dilute	A
Acetophenone	C
Acetyl Salicylic Acid	A
Acetyl Chloride, dry	A
Acetyl Chloride	D
Acetylene	A
Acid Fumes	A
Acrylonitrile	B
Adipic Acid	A
Alcohols, Allyl	A
Alcohols: Amyl	A
Alcohols: Benzyl	A
Alcohols: Butyl	A
Alcohols: Diacetone	A
Alcohols: Ethyl	A
Alcohols: Furfuryl, aqueous	A
Alcohols: Isobutyl	A
Alcohols: Isopropyl	A

Chemical	Rating
Alcohols: Methyl	B
Alcohols: Propyl (1-Propanol)	A
Aliphatic Esters	A
Alum, aqueous	A
Allyl Alcohol	A
Allyl Chloride	A
Alum, aqueous	A
Aluminum Acetate	A
Aluminum Chloride, 20% aqueous	A
Aluminum Chloride, aqueous	A
Aluminum Fluoride, aqueous	A
Aluminum Hydroxide	A
Aluminum Nitrate, aqueous	A
Aluminum Potassium Sulfate, 10%	B
Aluminum Sulfate, 10% aqueous	A
Aluminum Sulfate, aqueous	A
Aminoacetic Acid (glycine)	A
Ammonia, 10%	A
Ammonia Nitrate	A
Ammonia, anhydrous	A
Ammonia, aqueous	A
Ammonia, gas	A
Ammonia, liquid dilute	A
Ammonia, liquid	D
Ammonium Acetate	A
Ammonium Bifluoride	A
Ammonium Carbonate	A
Ammonium Chloride, 10% aqueous	A
Ammonium Chloride, aqueous	A
Ammonium Fluoride, aqueous	A
Ammonium Hydroxide, aqueous	A
Ammonium Nitrate, 10%	A
Ammonium Nitrate	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Ammonium Persulfate, aqueous	A
Ammonium Phosphate, dibasic	A
Ammonium Sulfate	A
Ammonium Sulfide	A
Amyl Acetate	A
Amyl Alcohol	A
Amyl Chloride	A
Aniline, dilute	A
Aniline, pure	A
Aniline Hydrochloride, aqueous	A
Aniline Oil	A
Animal Oils	A
Anone (cyclohexanone)	D
Antimony Chloride, aqueous	A
Antimony Trichloride	A
Aqua Regia (80% HCl, 20% HNO ₃)	A
Argon Gas, pure	A
Aromatic Solvents	A
Arsenic Acid, aqueous	A
Ascorbic Acid	A
Asphalt	A
Baking Soda, aqueous	A
Barium Carbonate	A
Barium Chloride, aqueous	A
Barium Hydroxide	A
Barium Sulfate	A
Barium Sulfide	A
Battery Acid (sulfuric acid, 20%)	A
Bay Oil	A
Beer	A
Beet Sugar Liquids	A
Benzaldehyde, aqueous	A
Benzalkonium Chloride, dilute	B

<i>Chemical</i>	<i>Rating</i>
Benzene	A
Benzene, pure	C
Benzene Sulfonic Acid, aqueous	A
Benzoic Acid	A
Benzol	A
Benzyl Alcohol	A
Benzyl Chloride	A
Benzyl Ether	A
Benzylamine, aqueous dilute	A
Biodiesel (fatty acid methyl ester)	A
Bisulfite	A
Bleach	A
Bone Oil	A
Borax (sodium borate)	A
Boric Acid, 10%	A
Boric Acid	A
Boron Hydrofluoric Acid	A
Brine (cooling brine)	A
Brines, saturated	A
Bromine Gas	A
Bromine Liquid, tech	A
Bromine Water, saturated aqueous	A
Butadiene	A
Butane Gas	A
Butanediol, 10% aqueous	A
Butanol (butyl alcohol)	A
Butyl Acetate, dilute	A
Butyl Acetate, pure	A
Butyl Alcohol	A
Butyl Amine, aqueous dilute	A
Butyl Ether, dilute	A
Butyl Phthalate	B
Butylene	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
 ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Butyric Acid	A
Butyric Acid, 20%	A
Calcium Bisulfide	A
Calcium Bisulfite, aqueous	A
Calcium Bromide, 38%	A
Calcium Carbonate (chalk) CaCO ₃	A
Calcium Chlorate, aqueous	A
Calcium Chloride, 10% aqueous	A
Calcium Chloride, aqueous	A
Calcium Hydroxide (lye), 10% aqueous	A
Calcium Hydroxide (lye)	B
Calcium Hypochlorite, aqueous	A
Calcium Nitrate, aqueous	A
Calcium Oxide (unslaked lime) CaO	A
Calcium Sulfate, 10%	A
Calcium Sulfate	A
Calcium Sulfide	A
Cane Juice	A
Car Antifreeze	A
Carbolic Acid (phenol)	A
Carbon Dioxide, dry	A
Carbon Dioxide, wet	A
Carbon Disulfide	B
Carbon Monoxide Gas	B
Carbon Tetrachloride	A
Carbon Tetrachloride, dry	A
Carbon Tetrachloride, wet	A
Carbonated Water (carbonic acid)	A
Carbonic Acid (carbonated water)	A
Carbonyl Chloride Gas (phosgene)	A
Castor Oil	A
Caustic Potash, aqueous	B
Caustic Soda (sodium hydroxide)	A

<i>Chemical</i>	<i>Rating</i>
Cellosolve (glycol ethyl ether)	A
Cellulose Acetate	D
Chloral Hydrate	D
Chlorates of Na, K, Ba	A
Chloric Acid, aqueous	A
Chlorides of Na, K, Ba	A
Chlorinated Lime, aqueous	A
Chlorine Gas, dry 10%	A
Chlorine Gas, dry	A
Chlorine Gas, wet	B
Chlorine Dioxide, 8% aqueous solution	A
Chlorine Water (5-10 ppm)	B
Chlorine, anhydrous liquid	A
Chlorine Bleaching Lye	B
Chloroacetic Acid, aqueous	A
Chlorobenzene (mono)	A
Chloroethanol (ethylene chlorohydrin)	A
Chlorofluorocarbons	C
Chloroform (trichloromethane)	A
Chloromethane (methyl chloride)	D
Chlorosulfonic Acid	D
Chrome Alum, aqueous	A
Chromic Acid, 5% aqueous	A
Chromic Acid, 10% aqueous	A
Chromic Acid, 30% aqueous	A
Chromic Acid, 50% aqueous	A
Chromic Acid, 80%	B
Cider	A
Citric Acid, 10% aqueous	A
Citric Acid, aqueous	A
Citrus Oil or Terpene (d-Limonene)	A
Clorox® Bleach	A
Coal Gas	B

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)

A = Excellent

B = Good - Minor Effect, slight corrosion or discoloration

C = Fair - Moderate Effect, not recommended

D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Coconut Oil	A
Colophonium (tall oil)	A
Cooling Brine	A
Copper Acetate, aqueous	A
Copper Chloride, aqueous	A
Copper Cyanide	A
Copper Nitrate, aqueous	A
Copper Salts (most)	A
Copper Sulfate, 5% aqueous	A
Copper Sulfate, >5% aqueous	A
Cottonseed Oil	A
Cresols, aqueous	B
Cresylic Acid	B
Cresylic Acids, 50%	B
Crotonaldehyde	A
Cyclohexane	A
Cyclohexanol	A
Cyclohexanone (anone)	D
Detergents	A
Detergents, synthetic	A
Dextrin, aqueous	A
Dextrose (glucose)	A
Dextrose (glucose), aqueous	A
Diacetone Alcohol	D
Dibenzyl Ether	A
Dibutyl Phthalate	D
Dibutyl Sebacate	D
Dibutylamine, aqueous	A
Dichlorobenzene	A
Dichloroethane (ethylene chloride)	A
Dichloromethane (methylene chloride)	D
2,2-Dichloropropionic Acid	A
Diesel Fuel (20, 30, 40, 50)	A

<i>Chemical</i>	<i>Rating</i>
Diesel Oil	A
Diethanolamine, aqueous dilute	A
Diethyl Ether (ether)	B
Diethyl Malonate	D
Diethylamine, aqueous	D
Diethylene Glycol	A
Diethylenetriamine, aqueous	A
Diglycolic Acid	A
Diisobutyl Ketone, dilute	A
Diisopropyl Ketone, dilute	A
Dimethyl Acetamide	D
Dimethyl Aniline	A
Dimethyl Formamide	D
Dimethyl Phthalate, dilute	A
Dimethyl Sulfate	A
Dimethyl Sulfoxide, dilute	A
Dimethyl Sulfoxide, pure	D
Dimethylamine, aqueous	A
Dimethylamine, pure	D
Dimethylaniline	A
Dimethylformamide (DMF), pure	D
Dinitrogen Monoxide (nitrous oxide)	B
Dioctyl Phthalate	A
Dioctyl Phthalate, pure	C
Dioxane, pure	D
Diphenyl Oxide	B
Dipropylene Glycol Methyl Ether, dilute	A
Disodium Phosphate	A
Divinyl Benzene	A
Edible Oils	A
Emulsifiers, concentrated	A
Engine Oils	A
Epichlorohydrin, dilute	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
 ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Epsom Salts, aqueous	A
Essential Oils	A
Esters	B
Ethane, dilute	A
Ethane, pure	D
Ethanedioic Acid (oxalic acid), aqueous	A
Ethanol (ethyl alcohol)	A
Ethanolamine, aqueous	C
Ethanolamine, pure	C
Ethenylbenzene (styrene)	A
Ether (diethyl ether)	B
Ethyl Acetate	D
Ethyl Acetoacetate	A
Ethyl Acrylate	B
Ethyl Alcohol (ethanol)	A
Ethyl Benzoate	D
Ethyl Chloride	A
Ethyl Chloroacetate	A
Ethyl Chloroformate	A
Ethyl Cyanoacetate	A
Ethyl Ether	A
Ethyl Formate	A
Ethylbenzene	A
Ethylene	A
Ethylene Bromide	A
Ethylene Chloride (dichloroethane)	A
Ethylene Chlorohydrin, aqueous	A
Ethylene Diamine	B
Ethylene Dichloride	A
Ethylene Glycol, aqueous	A
Ethylene Glycol, pure	A
Ethylene Oxide Gas (EtO), dry 3%	A
Ethylene Oxide Gas	A

<i>Chemical</i>	<i>Rating</i>
Exhaust Fumes (with hydrogen fluoride)	A
Exhaust Fumes (with carbon dioxide)	A
Exhaust Fumes (with carbon monoxide)	A
Exhaust Fumes (with nitrous gases)	A
Exhaust Fumes (with hydrochloric acid)	A
Exhaust Fumes (with sulfur dioxide, dry)	A
Exhaust Fumes (with sulfur trioxide, dry)	A
Exhaust Fumes (with sulfuric acid, wet)	A
Fatty Acid Methyl Ester (biodiesel)	A
Fatty Acid Sulfates, aqueous	A
Fatty Acids (greases)	A
Fatty Acids, >C6	A
Ferric Chloride, 10%	A
Ferric Chloride, aqueous	A
Ferric Nitrate, aqueous	A
Ferric Sulfate	A
Ferrous Chloride, chloride	A
Ferrous Sulfate	A
Fluoboric Acid	A
Fluorinated Refrigerants	A
Fluorine	A
Fluorine Gas, dry pure	D
Fluorine Gas, wet pure	C
Fluoroboric Acid	A
Fluosilicic Acid, 20%	A
Fluosilicic Acid, 100%	A
Food Fats and Oils	A
Formaldehyde, 40%	A
Formaldehyde, 100%	A
Formaldehyde Solution, aqueous	A
Formalin	A
Formic Acid, 10% aqueous	A
Formic Acid, aqueous	B

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
 ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Formic Acid, pure	C
Freon 11	A
Freon 12	A
Freon 22	A
Freon 113	B
Freon TF	B
Fruit Juices	A
Fuel Oils (1, 2, 3, 5A, 5B, 6)	B
Fuming Sulfuric Acid, pure	D
Furan, dilute	A
Furan Resin	D
Furfural (ant oil) C ₅ H ₄ O ₂	B
Furfuryl Alcohol, aqueous	A
Gallic Acid, 5%	A
Gallic Acid	A
Gasoline, high-aromatic	A
Gasoline, leaded	A
Gasoline, unleaded	A
Gelatin, aqueous	A
Ginger Oil	A
Glucose (dextrose)	A
Glue, PVA (polyvinyl acetate)	A
Glycerin, aqueous	A
Glycine (aminoacetic acid), aqueous	A
Glycolic Acid	B
Glycol Ethyl Ether (cellosolve)	A
Glycols	A
Gold Monocyanide	A
Grape Juice	A
Grape Vinegar, 5%	A
Grease	A
Greases (fatty oils)	A
Grid Gas	B

<i>Chemical</i>	<i>Rating</i>
Helium, pure	A
Heptane	A
Hexachloro-1,3-butadiene	A
Hexamethylenediamine, dilute	A
Hexamethylphosphortriamide, dilute	A
Hexamine	C
Hexane	A
Honey	A
Hydraulic Oil, petroleum	A
Hydraulic Oil, synthetic	A
Hydrazine (diamine), aqueous	A
Hydrazine Dihydrochloride, aqueous	A
Hydrazine Hydrate, aqueous	C
Hydrobromic Acid, 20%	A
Hydrobromic Acid, 50%	A
Hydrobromic Acid, 100%	A
Hydrochloric Acid, 10%	A
Hydrochloric Acid, 20%	A
Hydrochloric Acid, 37%	A
Hydrochloric Acid, 100%	A
Hydrochloric Acid, concentrated	A
Hydrochloric Acid, dry gas	A
Hydrocyanic Acid, aqueous	A
Hydrofluoric Acid, 20%	A
Hydrofluoric Acid, 40%	A
Hydrofluoric Acid, 50%	A
Hydrofluoric Acid, 75%	A
Hydrofluoric Acid, 100%	A
Hydrofluosilicic Acid, 20%	A
Hydrofluosilicic Acid, 100%	A
Hydrogen Chloride Gas, pure	B
Hydrogen Gas, pure	A
Hydrogen Peroxide, 10%	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)

A = Excellent

B = Good - Minor Effect, slight corrosion or discoloration

C = Fair - Moderate Effect, not recommended

D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Hydrogen Peroxide, 30%	A
Hydrogen Peroxide, 50%	A
Hydrogen Peroxide, 90%	A
Hydrogen Peroxide, 100%	A
Hydrogen Sulfide, aqueous	A
Hydrogen Sulfide Gas, dry	A
Hydroquinone, aqueous	A
Hydroxyacetic Acid, 70%	A
Hydroxybenzene (phenol)	A
Hypochlorites	A
Hypochlorites (Na 12-14%)	A
Hypochlorous Acid, aqueous	A
Illuminating Gas	B
Inert Gases, pure	A
Ink	A
Iodine	A
Iodine, in alcohol	A
Iodine Tincture	A
Iodoform	C
Iron Sulfate, aqueous	A
Isobutanol	A
Isobutyl Acetate	C
Isooctane	A
Isopropanol	A
Isopropyl Acetate	D
Isopropyl Chloride	A
Isopropyl Ether	D
Isopropylbenzene	A
Isotane	A
Jet Fuel (JP3, JP4, JP5)	B
Kerosene	A
Ketones	D
Lacquers	D

<i>Chemical</i>	<i>Rating</i>
Lactic Acid, aqueous	B
Lard (animal fats)	A
Latex	A
Laughing Gas (nitrous oxide)	B
Laundry Detergent	A
Lead Acetate, aqueous	A
Lead Nitrate, aqueous	A
Lead Sulfamate	A
Lemon Oil	A
Light Petroleum (petroleum spirits)	A
Ligroin	A
Lime (CaO)	A
Lime Water, aqueous	B
Linoleic Acid	A
Linseed Oil	A
Lithium Chloride, aqueous	A
Lubricants	A
Lubricating Oils, with aromatic additives	A
Lye (Ca(OH) ₂ , calcium hydroxide)	A
Lye (KOH, potassium hydroxide)	A
Lye (NaOH, sodium hydroxide)	D
Lysol	B
Machine Oils	A
Magnesium Carbonate	A
Magnesium Chloride, 10%	A
Magnesium Chloride, aqueous	A
Magnesium Hydroxide, 10% aqueous	A
Magnesium Hydroxide, aqueous	A
Magnesium Nitrate, aqueous	A
Magnesium Sulfate, aqueous	A
Maleic Acid, aqueous	A
Maleic Anhydride	A
Malic Acid (apple acid), aqueous	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
 ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Manganese Sulfate, aqueous	A
Marsh Gas (methane)	B
Mash, fermented	A
Mayonnaise	A
Meat Juices	A
Mercaptane	C
Mercuric Chloride, dilute aqueous	A
Mercuric Cyanide	A
Mercurous Nitrate, aqueous	A
Mercury	A
Mercury Salts, aqueous	A
Methacrylic Acid	A
Methane Gas	B
Methanoic Acid, 10% aqueous	A
Methanoic Acid, aqueous	A
Methanol (methyl alcohol)	B
Methyl Acetate	B
Methyl Acetone (mixture)	D
Methyl Acrylate	B
Methyl Alcohol, 10%	A
Methyl Bromide	A
Methyl Butyl Ketone	D
Methyl Cellosolve	A
Methyl Chloride (chloromethane)	D
Methyl Chloroacetate	A
Methyl Chloromethyl Ether	A
Methyl Dichloride	D
Methyl Ethyl Ketone (MEK, butanone)	D
Methyl Isobutyl Ketone	D
Methyl Isopropyl Ketone	A
Methyl Methacrylate	B
Methylamine, dilute	C
Methylene Chloride	D

<i>Chemical</i>	<i>Rating</i>
Milk	A
Milk Products	A
Mine Gas (methane)	B
Mineral Oil	A
Mineral Water	A
Moist Air	A
Molasses	B
Molasses Based Flavoring	A
Monochloroacetic Acid	B
Monoethanol Amine	C
Morpholine, aqueous	B
Motor Oil	B
Mustard	A
Naphtha	A
Naphthalene	A
Natural Gas (methane)	B
Nickel Chloride, aqueous	A
Nickel Nitrate, aqueous	A
Nickel Salts	A
Nickel Sulfate, aqueous	A
Nicotine	A
Nitrates of Na, K and NH3	A
Nitric Acid, 5-10%	A
Nitric Acid, 20%	A
Nitric Acid, 50%	A
Nitric Acid, concentrated	A
Nitric Acid, fuming dilute	A
Nitrite (Na)	A
Nitrobenzene	A
Nitrobenzene, pure	C
Nitroethane	A
Nitrogen Gas, pure	A
Nitrogen Oxides (nitrous fumes)	C

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
 ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Nitromethane	A
Nitrotoluenes, pure	B
Nitrous Acid	B
Nitrous Fumes (nitrogen oxides)	C
Nitrous Oxide (dinitrogen monoxide)	B
Oils: Aniline	A
Oils: Animal	A
Oils: Bay	A
Oils: Bone	A
Oils: Castor	A
Oils: Citric	A
Oils: Coconut	A
Oils: Cod Liver	A
Oils: Corn	A
Oils: Cottonseed	A
Oils: Crude Oil	A
Oils: Diesel Fuel (20, 30, 40, 50)	A
Oils: Edible	A
Oils: Engine	A
Oils: Essential	A
Oils: Fuel (1, 2, 3, 5A, 5B, 6)	B
Oils: Ginger	A
Oils: Hydraulic Oil, petroleum	A
Oils: Hydraulic Oil, synthetic	A
Oils: Lemon	A
Oils: Linseed	A
Oils: Lubricating, with aromatic additives	A
Oils: Machine	A
Oils: Mineral	A
Oils: Olive	A
Oils: Orange	A
Oils: Palm	A
Oils: Paraffin	A

<i>Chemical</i>	<i>Rating</i>
Oils: Peanut	A
Oils: Peppermint	A
Oils: Pine	A
Oils: Rapeseed	A
Oils: Rosin	A
Oils: Sesame Seed	A
Oils: Silicone	A
Oils: Soybean	A
Oils: Spindle	A
Oils: Tanning	A
Oils: Transformer	A
Oils: Turbine	A
Oils: Turpentine	A
Oils: Vegetable	A
Oleic Acid	A
Oleum, 25%	C
Oleum, pure	D
Olive Oil	A
Orange Oil	A
Oxalic Acid, cold 10%	B
Oxalic Acid, cold	B
Oxygen Gas, pure	D
Ozone Gas	A
Ozone Gas, dry	A
Ozone Gas, wet	A
Palm Oil	A
Palmitic Acid	A
Paraffin	A
Paraffin Oil	A
Paraffin Wax	A
Peanut Oil	A
Pentane (amyl hydride) C5H12	A
Peppermint Oil	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)

A = Excellent

B = Good - Minor Effect, slight corrosion or discoloration

C = Fair - Moderate Effect, not recommended

D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Peracetic Acid (peroxyacetic acid)	A
Peracetic Acid, 6% aqueous	B
Perchloric Acid	A
Perchloroethylene, pure	B
Peroxyacetic Acid (peracetic acid)	A
Peroxyacetic Acid, 6% aqueous	B
Petrolatum	A
Petroleum	A
Petroleum Spirits	A
Phenol, 10% (carbolic acid)	A
Phenol (carbolic acid)	A
Phenyl Ether	A
Phenylethene (styrene)	A
Phenylhydrazine	A
Phenylhydrazine Hydrochloride, aqueous	A
Phosgene Gas (carbonyl chloride)	A
Phosphoric Acid, 20%	B
Phosphoric Acid, >40%	B
Phosphoric Acid, crude	A
Phosphoric Acid, S40%	B
Phosphoric Acid Anhydride	D
Phosphorus, red	A
Phosphorous Chlorides	B
Phosphorous Oxychloride, dilute	A
Phosphorous Pentoxide	A
Phosphorus Trichloride	A
Photographic Developers	B
Photographic Emulsions	B
Photographic Fixing Baths	B
Photographic Solutions	B
Phthalic Acid	A
Phthalic Anhydride	A
Picric Acid (trinitrophenol)	A

<i>Chemical</i>	<i>Rating</i>
Pine Oil	A
Pinene (turpentine oil), pure	A
Potash (potassium carbonate), aqueous	B
Potassium Aluminum Sulfate, aqueous	A
Potassium Bicarbonate, aqueous	B
Potassium Bromate, aqueous	A
Potassium Bromide, aqueous	A
Potassium Carbonate (potash), aqueous	B
Potassium Chlorate, aqueous	B
Potassium Chloride, up to 30% aqueous	A
Potassium Chromate, aqueous	B
Potassium Cyanide Solutions, aqueous	A
Potassium Dichromate, aqueous	A
Potassium Ferricyanide, aqueous	A
Potassium Ferrocyanide, aqueous	A
Potassium Hydroxide, aqueous	B
Potassium Hypochlorite, aqueous	A
Potassium Iodide, aqueous	A
Potassium Manganate	A
Potassium Nitrate, 10% aqueous	A
Potassium Nitrite, aqueous	A
Potassium Permanganate, aqueous	A
Potassium Persulfate, aqueous	C
Potassium Phosphate, aqueous	B
Potassium Sulfate, aqueous	A
Potassium Sulfide, aqueous	A
Propane, gas	A
Propane, liquefied	A
Propanol, pure	A
Propyl Acetate	A
Propyl Alcohol, aqueous	A
Propylamine, dilute	A
Propylene (propene, methyl ethylene)	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)

A = Excellent

B = Good - Minor Effect, slight corrosion or discoloration

C = Fair - Moderate Effect, not recommended

D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Propylene Glycol, aqueous	A
Propylene Glycol, pure	A
Propylene Oxide, dilute	A
Pyridine (C ₅ H ₅ N), dilute	D
Pyrogallol, aqueous	A
Pyrogallol, aqueous	A
Rapeseed Oil	A
Red Prussiate of Potash, aqueous	A
Rosin Oil	A
Salicylaldehyde	A
Salicylic Acid	A
Salt Brine (NaCl saturated)	A
Salt Cake (sodium sulfate), aqueous	A
Sea Water	A
Silicic Acid	A
Silicone	A
Silicone Fluids	A
Silicone Oil	A
Silver Nitrate, aqueous	A
Soap Solutions, aqueous	A
Soda (sodium carbonate), aqueous	B
Soda Ash (sodium carbonate)	A
Soda Lye (sodium hydroxide), aqueous	A
Sodium Acetate, aqueous	A
Sodium Benzoate, aqueous	A
Sodium Bicarbonate, aqueous	A
Sodium Bisulfate, 10% aqueous	A
Sodium Bisulfate, aqueous	A
Sodium Bisulfite, aqueous	A
Sodium Borate (Borax)	A
Sodium Bromide, aqueous	A
Sodium Carbonate, aqueous	B
Sodium Chlorate, aqueous	A

<i>Chemical</i>	<i>Rating</i>
Sodium Chloride, aqueous	A
Sodium Chlorite, aqueous	A
Sodium Chromate, aqueous	A
Sodium Cyanide, aqueous	A
Sodium Dithionite, aqueous	A
Sodium Ferrocyanide, aqueous	A
Sodium Fluoride, aqueous	A
Sodium Hydrogen Carbonate, aqueous	A
Sodium Hydrogen Sulfate, aqueous	A
Sodium Hydrogen Sulfide, aqueous	A
Sodium Hydroxide, 20% aqueous	A
Sodium Hydroxide, 50% aqueous	C
Sodium Hydroxide, 80% aqueous	C
Sodium Hypochlorite, <20%, aqueous	B
Sodium Iodide, aqueous	B
Sodium Metaphosphate	A
Sodium Nitrate, aqueous	A
Sodium Nitrite, aqueous	B
Sodium Perborate, aqueous	B
Sodium Persulfate, aqueous	B
Sodium Peroxydisulfate, aqueous	B
Sodium Peroxide	A
Sodium Phosphate, aqueous	B
Sodium Polyphosphate	A
Sodium Propionate, aqueous	B
Sodium Silicate (water glass), aqueous	A
Sodium Sulfate (thenardite), aqueous	A
Sodium Sulfide, aqueous	B
Sodium Sulfite, aqueous	A
Sodium Thiosulfate, aqueous	A
Soluble Glass (sodium silicate), aqueous	A
Soybean Oil	A
Spindle Oils	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
 ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Stannic Chloride	A
Stannous Chloride	A
Starch	A
Starch Solution, aqueous	A
Stearic Acid, pure	A
Stoddard's Solvent	A
Styrene (vinylbenzene), pure	A
Succinic Acid, aqueous	B
Sugar, Syrups and Jams	A
Sugar Solutions	A
Sulfamic Acid	A
Sulfate Liquors	A
Sulfite Liquors	A
Sulfites	A
Sulfonic Acids	A
Sulfur	A
Sulfur Chloride, pure	A
Sulfur Dichloride	A
Sulfur Dioxide, liquid pure	A
Sulfur Dioxide Gas, dry	A
Sulfur Dioxide Gas, wet	A
Sulfur Dioxide, 96%	A
Sulfur Hexafluoride, pure	B
Sulfur Trioxide	D
Sulfur Trioxide, dry	C
Sulfuric Acid, <10%	A
Sulfuric Acid, 10-75%	A
Sulfuric Acid, 75-100%	A
Sulfuric Acid, cold concentrated	A
Sulfuric Acid, fuming	D
Sulfurous Acid, 10%	A
Sulfur Chlorides	D
Sulfuryl Chloride, dilute	A

<i>Chemical</i>	<i>Rating</i>
Table Salt (sodium chloride), aqueous	A
Tall Oil (colophonium)	A
Tallow	A
Tannic Acid, 10% aqueous	B
Tanning Oil	A
Tartaric Acid, aqueous	B
Tetrachloroethane	A
Tetrachloroethylene, pure	B
Tetraethyl Lead, pure	B
Thenardite (sodium sulfate), aqueous	A
Trichlorethylene	A
Tetrahydrofuran, aqueous	B
Thioglycol	A
Thionyl Chloride, dilute	A
Thiophosphoryl Chloride, dilute	A
Tin Chlorides, aqueous	A
Tin Salts, aqueous	A
Toluene (toluol)	A
Toluenesulfonyl Chloride	A
Tomato Juice	A
Town Gas	B
Transformer Oil	A
Tributyl Phosphate, dilute	A
Tributyl Phosphate, pure	D
Trichloroacetic Acid, aqueous	B
Trichloroethane	A
Trichloroethylene	B
Trichloromethane (chloroform)	A
Tricresyl Phosphate, dilute	D
Triethanolamine, aqueous	A
Triethylamine	A
Trifluoroacetic Acid	A
Trimethylamine, aqueous	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)
A = Excellent
B = Good - Minor Effect, slight corrosion or discoloration
C = Fair - Moderate Effect, not recommended
D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
 ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.

PVDF (Kynar®) Chemical Compatibility Chart

ver 28-Oct-2022

<i>Chemical</i>	<i>Rating</i>
Trinitrophenol (picric acid)	A
Trisodium Phosphate	A
Turpentine (COH16)	A
Turpentine Oil (pinene)	A
Turpentine Substitute (white spirit)	A
Urea, 30% aqueous	A
Urine	A
Varnish	A
Vegetable Oils	A
Vinegar	B
Vinegar, grape, 5%	A
Vinyl Acetate	B
Vinyl Chloride	B
Vinylbenzene (styrene), pure	A
Water, acid mine	A
Water, deionized	A
Water, distilled	A
Water, fresh	A

<i>Chemical</i>	<i>Rating</i>
Water, hard	A
Water, mineral	A
Water, salt	A
Water, soft	A
Water Glass (sodium silicate), aqueous	A
Water Vapor	A
Wetting Agents, <5%	A
Whiskeys (dependent on ingredients)	A
White Liquor, pulp mill	A
White Spirit	A
Wines	A
Xenon Gas, pure	A
Xylene (xylol, dimethylbenzene)	B
Yeast, aqueous	A
Yellow Prussiate of Potash	A
Zinc Chloride, 10%	A
Zinc Sulfate, 10%	A

Key to General Chemical Resistance – All data is based on ambient or room temperature conditions, about 64°F (18°C) to 73°F (23°C)

A = Excellent

B = Good - Minor Effect, slight corrosion or discoloration

C = Fair - Moderate Effect, not recommended

D = Severe Effect, not recommended for ANY use

It is the sole responsibility of the system designer and user to select products suitable for their specific application requirements and to ensure proper installation, operation, and maintenance of these products. Material compatibility, product ratings and application details should be considered in the selection. Improper selection or use of products described herein can cause personal injury or product damage.



Industrial Specialties Mfg. and IS Med Specialties

End your search, simplify your supply chain
ISO 9001:2015 Certified Companies

4091 S. Eliot St., Englewood, CO 80110-4396

Phone 303-781-8486 | Fax 303-761-7939

industrialspec.com | ismedspec.com

© Copyright 2022 Industrial Specialties Mfg.